

Marketing Department
832-445-3300

Customer Specification

9999
General Spec Customer

Date printed	08/13/2012
Specification	General Spec Customer
Date	17-APR-12
Revision	08
Customer Material	
Material Description	CX N550 BDS-25 KG-K323-1000 KG-W

Characteristic	Unit	Reference	Min	Target	Max
Iodine Adsorption Number	g/kg		38.0	43.0	48.0
Oil Absorption Number	cc/100		116.0	121.0	126.0
Heating Loss (125degC)	%		0.00	0.00	1.00
Pelleted Fines 5'	%		0.0	0.0	12.0
Sieve residue (35M %)	%		0.0000	0.0000	0.0010
Sieve residue (325M %)	%		0.0000	0.0000	0.0500
Transmittance at 425nm	%		80.0	100.0	100.0
Pour Density (lb/ft3)	lb/ft3		19.0	22.0	25.0
Ash Content	%		0.00	0.00	1.00
Pellet Hardness (High)	g		0		80
Pellet Hardness (Avg)	g		0		40
Crushed OAN	cc/100		80.0	85.0	90.0
Tint Strength, IRB=100%	%		50.0	55.0	60.0
Nitrogen Surface Area, BET	m2/g		35.0	40.0	45.0
STSA, Corrected	m2/g		34.0	39.0	44.0

All warranty claims in respect of the conformance of our product are subject to our terms of contract and General terms and Conditions of Sale and Delivery. The data listed above reflects the criteria for our internal quality tests. We do not hereby make any express or implied warranty, whether for specific properties or for fitness for any particular application or purpose. All values are valid for the product when dispatched from the plants.